

45 Higgins Avenue Winnipeg, MB R3B 0A8 Tel: 204.339.6456 Fax: 204.334.1800

www.duxtonwindows.com

Thermal Performance SERIES 328 - FiberWall [™] Fixed

				Centre-of-Glass				Overall Window				Energy Star	
Glass type	Application	LoĒ Surface	Gas	R- Value	U- Value	Heat Gain	Visible Light	U-Value (imperial)	U-Value (metric)	Heat Gain	Visible Light	Energy Rating (ER)	Energy Star Efficiency
Dual Pane													
Cardinal LoĒ-180	High Solar Gain	3	Argon	3.85	0.26	0.68	79%	0.28	1.59	0.61	70%	40	••
Cardinal LoĒ-272	Mid-Range	2	Argon	4.00	0.25	0.41	72%	0.27	1.53	0.36	63%	-	0
Cardinal LoĒ-366	Low Solar Gain	2	Argon	4.17	0.24	0.27	65%	0.26	1.48	0.24	57%	-	0
Triple Pane - 1 LoĒ Coating - High Performance													
Cardinal LoĒ-180	High Solar Gain	5	Argon	5.56	0.18	0.61	73%	0.20	1.14	0.54	64%	46	• •
Cardinal LoĒ-272	Mid-Range	2	Argon	5.26	0.19	0.38	66%	0.20	1.14	0.34	58%	34	•
Cardinal LoĒ-366	Low Solar Gain	2	Argon	5.56	0.18	0.25	59%	0.20	1.14	0.22	52%	28	•
Triple Pane - 2 LoĒ Coatings - Ultra High Performance													
Cardinal LoĒ-180 and 180	High Solar Gain	2 and 5	Argon	7.69	0.13	0.56	70%	0.16	0.91	0.50	61%	49	••
Cardinal LoĒ-272 and 180	Mid-Range	2 and 5	Argon	7.69	0.13	0.37	63%	0.15	0.85	0.33	56%	40	••
Cardinal LoĒ-272 and 272	Mid-Range	2 and 5	Argon	7.69	0.13	0.35	58%	0.15	0.85	0.31	51%	39	• •
Cardinal LoĒ-366 and 180	Low Solar Gain	2 and 5	Argon	7.69	0.13	0.24	57%	0.15	0.85	0.22	50%	34	••
Cardinal LoĒ-366 and 366	Low Solar Gain	2 and 5	Argon	8.33	0.12	0.24	47%	0.14	0.79	0.21	41%	35	••

Performance Values are calcuated by certified, 3rd party test labs. Information is gleaned from best available industry sources. The reader is cautioned that test results should be used for comparison purposes only. Results are size and installation dependent. In-service performance can be significantly different from those shown. Product tested indicates design potential. Model size was 1200 mm x 1500 mm.



45 Higgins Avenue Winnipeg, MB R3B 0A8 Tel: 204.339.6456 Fax: 204.334.1800

www.duxtonwindows.com

Thermal Performance SERIES 328 - FiberWall [™] Fixed

Notes

- (1) 2-Pane calculations based on 2 tempered lites of 1/8" (3 mm) glass and 3/4" (20 mm) airspace.
- (2) 3-Pane calculations based on 3 tempered lites of 1/8" (3 mm) glass and two 1/2" (13 mm) airspaces.
- (3) Calculations for argon filled unit made with 90% Argon/ 10% air.
- (4) NFRC Environmental Conditions used for all values.
- (5) Cardinal Endur warm edge stainless steel spacer used for all values.
- (6) Thicker glass options available, up to 6 or 8 mm.
- (7) Chart indicating Energy Star Canada efficiency designation:
 - ENERGY STAR Most Efficient 2023
 - ENERGY STAR
 - Not Applicable

Values updated August 2023.